3M™ Scotchshield™ Safety and Security Window Film

Ultra S800

Technical Data

Product Features & Benefits

- Micro-layered film designed for tear resistance
- Optically clear
- Applies to interior glass surfaces
- Helps protect from broken glass hazards
- Helps extend the life of furnishings by significantly reducing harmful UV rays

Applications

- Bomb Blast Mitigation
- Safety Glazing
- Helping to Deter Break & Entry
- Building Envelope Protection
- Spontaneous Glass Breakage
- Seismic Preparedness

Performance Testing*

| errormance resting | | | | |
|-------------------------------|---------------------------|--------------------|-----------------------------|-------------------------------------|
| Method | Glass Substrate | Film Attachment | | Rating |
| Safety Glazing | | | | |
| 16 CFR 1201 | 1/4" & 1/8" annealed | | Category 2, 400 ft-lbs | |
| ANSI Z97.1 | 74 & 176 affilealed | | Clas | ss A (Unlimited), 400 ft-lbs |
| Impact Resistance | | | | |
| ASTMs E1886 / E1996 | ¼" tempered | IPA | Large Missile C, +/- 75 psf | |
| ASTM E330 | 3/16" tempered | IFA | +/- 100 psf | |
| Blast Mitigation | | Blast Load Rating | | |
| | 1/4" annealed | IPA | 9 psi, 60 psi*msec | GSA Level 2 / ASTM "Minimal Hazard" |
| | 74 aririealeu | IPP | 7 psi, 42 psi*msec | GSA Level 2 / ASTM "Minimal Hazard" |
| GSA TS01-2003 / ASTM F1642 | ¼" tempered | IPA | 9 psi, 60 psi*msec | GSA Level 2 / ASTM "No Hazard" |
| | | IPP | 7 psi, 42 psi*msec | GSA Level 2 / ASTM "Minimal Hazard" |
| | 1" double pane (annealed) | IPA | 10 psi, 80 psi*msec | GSA Level 2 / ASTM "No Hazard" |
| | | IPP | 9 psi, 60 psi*msec | GSA Level 2 / ASTM "Minimal Hazard" |

*Glazing systems vary. Contact 3M for more information

Film Properties (nominal)

| Film Thickness | 8 mils | | | | |
|--------------------------------|---------------|--|--|--|--|
| Film Construction | Micro-layered | | | | |
| Tensile Properties (ASTM D882) | | | | | |
| Tensile Strength | 32,000 psi | | | | |
| Break Strength | 255 lbs/in | | | | |
| Elongation at Break | 130% | | | | |
| Yield Strength | 15,000 psi | | | | |
| Elongation at Yield | 9% | | | | |
| Modulus | 473 kpsi | | | | |

| Graves Area Tear Resistance (ASTM D1004) | 1,200 lbs% | | | |
|---|------------|--|--|--|
| Puncture-Propagation-Tear Resistance (ASTM D2582) | 9.5 lbf | | | |
| Puncture Strength (ASTM D4830) | 185 lbf | | | |
| Abrasion Resistance (ASTM D1044) | 3% ∆ haze | | | |
| Peel Strength (ASTM D3330) | 6 lb/in | | | |
| Flammability (ASTM E84) | Class A | | | |
| Solar Properties – film applied to ¼" clear glass | | | | |
| Visible Light Transmitted | 87% | | | |
| UV Light Rejected | 99.9% | | | |

IMPORTANT NOTICE:

This product is **not approved** in the State of Florida for use as hurricane, windstorm, or impact protection from wind-borne debris from a hurricane or windstorm. In compliance with Florida Statute 553.842, this product may not be advertised, sold, offered, provided, distributed, or marketed in the State of Florida as hurricane, windstorm, or impact protection from wind-borne debris from a hurricane or windstorm.

The information provided in this report is believed to be reliable; however, due to the wide variety of intervening factors, 3M does not warrant that the results will necessarily be obtained. All details concerning product specifications and terms of sale are available from 3M.

Renewable Energy Division St. Paul, MN 55144-1000 1-866-499-8857 www.3M.com/windowfilm

3M is a trademark of 3M Company. © 3M 2016. All rights reserved.

72